

# SEMI-PROFESSIONAL SCUOLA WATERCOLORS TECHNICAL INFORMATION

FORMULATED WITH THE MOST PERMANENT (LIGHTFAST) PIGMENTS

ALL NON TOXIC COLORS

HEALTH LABELING CONFORMS TO ASTM D-4236

ITEM No.	COLOR NAME	S	LF	COLOR INDEX NAME	COLOR INDEX NUMBER	COMMON NAME
602	Alizarin Crimson (Quinacridone)	2	II	PV 19	73900	Quinacridone Violet
605	Burnt Sienna	1	I	PBr 7	77491	Burnt Sienna
606	Burnt Umber	1	I	PBr 7	77491	Burnt Umber
608	Cadmium Orange (Hue)	2	I	PO 62	11775	Benzimidazolone Or.H5G
612	Cadmium Red Light (Hue)	2	II	PR188	12467	Naphthol AS
615	Cadmium Yellow Deep (Hue)	2	II	PY 97 PO 62	11767 11775	Arylide Yellow FGL Benzimidazolone Or.H5G
617	Cadmium Yellow Light (Hue)	2	II	PY 97 PO 62	11767 11775	Arylide Yellow FGL Benzimidazolone Or.H5G
630	Cerulean Blue (Hue)	2	II	PB 15 PW 6	74160 77891	Phthalo Blue Titanium White
634	Cobalt Blue (Hue)	2	II	PB 15 PW 6	74160 77891	Phthalo Blue Titanium White
639	Gamboge (Hue)	2	II	PY 3 PY 42	11710 77492	Arylide Yellow 10G Iron Oxide Yellow
642	Hansa Yellow Light	2	II	PY 3	11710	Arylide Yellow 10G
644	Hooker's Green Light	2	I	PG 7 PY 42	74260 77492	Phthalo Green Iron Oxide Yellow
651	Lamp Black	1	I	PBk 6	77266	Lamp Black
656	Mauve	2	II	PV 19 PB 29	73900 77007	Quinacridone Violet Ultramarine Blue
661	Payne's Gray	2	I	PBk 6 PB 27	77266 77510	Lamp Black Prussian Blue
665	Permanent Red	2	II	PR 188	12467	Naphthol AS
667	Phthalo Blue	2	II	PB 15	74160	Phthalocyanine Blue
668	Phthalo Green	2	I	PG 7	74260	Phthalo Green
671	Prussian Blue	2	I	PB 27	77510	Prussian Blue
673	Raw Sienna	1	I	PBr 7	77491	Raw Sienna
674	Raw Umber	1	I	PBr 7	77491	Raw Umber
676	Red Rose Deep (Quinacridone)	2	II	PV 19	73900	Quinacridone Violet
677	Sap Green	2	I	PG 7 PY 42	74260 77492	Phthalo Green Iron Oxide Yellow
682	Titanium White	1	I	PW 6	77891	Titanium White
684	Ultramarine Blue	2	I	PB 29	77007	Ultramarine Blue
688	Venetian Red	1	I	PR 101	77491	Venetian Red
690	Viridian Green	2	I	PG 7	74260	Phthalo Green
692	Yellow Ochre	1	I	PY 42	77492	Iron Oxide Yellow

Legend	Definition
S	Series Number
LF I	Lightfastness Excellent (as per ASTM D-5067)
LF II	Lightfastness Very Good (as per ASTM D-5067)
WA	Warm Hue
CL	Cool Hue
G1	Granulates Some for Texture and Dimension
G2	Granulates Well for Texture and Dimension

Legend	Definition
T	Transparent
ST	Semi-Transparent
O	Opaque
SO	Semi-Opaque
STA	Staining
LIF	Liftable
BL	Bleeds

THE INFORMATION CONTAINED HEREIN IS, TO OUR BEST KNOWLEDGE, TRUE AND ACCURATE. THE CHARACTERISTICS GIVEN ARE INTENDED AS GUIDE V ALL RECOMMENDATIONS AND SUGGESTIONS ARE MADE WITHOUT GUARANTEE. NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING THE ACCURACY SINCE THE CONDITIONS OF USE ARE BEYOND OUR CONTROL.

